



Hardie® Plank Lap Siding

Submittal Form

01

Submitted to: Derrick Pace	☐ HZ5® Product Zone ☑ HZ10® Product Zone
Project Name: 1015 N Main St	Product Width: ☐ 5-1/4in ☐ 6-1/4in ☐ 7-1/4in ☐ 8in ☑ 8-1/4in ☐ 9-1/4in ☐ 12in
Submitted by:	Product Finish: ✓ Primed □ColorPlus® Technology
Date: 10/29/2025	Product Texture: ✓ Smooth ☐ Select Cedarmill® ☐ Colonial Roughsawn® ☐ Colonial Smooth® ☐ Rustic Cedar

Hardie® Plank Lap Siding

Specification Sheet

01

DIVISION: 07 00 00 THERMAL AND MOISTURE PROTECTION

SECTION: 07 46 46 FIBER CEMENT SIDING

HARDIE® PLANK LAP SIDING

Manufacturer

James Hardie Building Products, Inc.

The products are manufactured at the following locations, with quality control inspections by ICC-ES:

- Cleburne, Texas
- Plant City, Florida
- Reno, Nevada
- Waxahachie, Texas
- Prattville, Alabama
- Peru, Illinois
- · Pulaski, Virginia
- Tacoma, Washington
- Fontana, California
- · Summerville, South Carolina

Compliance with the following codes

- 2006 thru 2021 International Building Code (IBC)
- 2006 thru 2021 International Residential Code (IRC)

For more information about other compliances and applicable uses, refer to ICC-ES ESR-2290

Features

- Noncombustible
- Dimensionally Stable
- Resists damage from pests
- Weather Resistant-Engineered for Climate®
- Impact resistant
- Sustainable

Use

Hardie® fiber-cement lap siding is used as exterior wall covering. The product complies with IBC Section 1403.9 and IRC Section R703.10. The product may be used on exterior walls of buildings of Type I, II, III and IV construction (IBC)

Description

Hardie® Plank lap siding is a single-faced, cellulose fiber-reinforced cement (fiber-cement) product. Hardie® Plank lap siding complies with ASTM C1186, as Grade II, Type A; has a flame-spread index of 0 and a smoke-developed index of 5 when tested in accordance with ASTM E84; and is classified as noncombustible when tested in accordance with ASTM E136.

Available Sizes

Width (in)	Length	Thickness (in)
5-1/4, 6-1/4,	12 feet	5/16
7-1/4, 8, 8-1/4,		
9-1/4, 12		
	5-1/4, 6-1/4, 7-1/4, 8, 8-1/4,	5-1/4, 6-1/4, 12 feet 7-1/4, 8, 8-1/4,

^{*} HZ5: 9-1/4, 12 only available primed HZ10: 5-1/4, 9-1/4, 12 only available primed.

Weight2.31 lbs. per square foot

Texture & Finish

Hardie® Plank lap siding comes in a variety of textures and finishes. The product is available in smooth or wood grain texture. Additional textures are available on a regional basis. Finish options are primed for field paint, or factory finished with ColorPlus® Technology. Color availability varies by region.

Engineered for Climate®

Hardie® Plank lap siding is engineered for performance to specific weather conditions by climate zones as identified by the following map.



SPECIFICATION SHEET 01 FEBRUARY 2024

Performance Properties

	General Property	Test Method	Unit or Characteristic	Requirement	Result
PHYSICAL ATTRIBUTES	Dimensional Tolerances ASTM C1185	'	Length	± 0.5% or ± 1/4 in	
			Width	± 0.5% or ± 1/4 in	
			Thickness	± 0.04 in	
		Squareness	Δ in diagonals \leq 1/32 in/ft of sheet length. Opposite sheet sides shall not vary in length by more than 1/32 in/ft	Pass	
			Edge Straightness	≤ 1/32 in/ft of length	
	Density, lb/ft ³	ASTM C1185		As reported	83
	Water Absorption, % by mass	ASTM C1185		As reported	36
	Water Tightness	ASTM C1185	Physical Observations	No drop formation	Pass
	Flexural Strength ASTM C1185	Wet conditioned, psi	>1015 psi	Pass	
	Tiexarai Girongin	exural Stretigiti ASTIVI CT 165		>1450 psi	1 433
THERMAL	Thermal Conductivity		(BTU/(hr·ft°F))/inch	As reported	2.07
	Actual Thermal Conductivity	ASTM C177	(K _{eff})		6.62
	Thermal Resistance	ASTIVICITI	$R=1/K_{eff}$		0.48
	Actual Thermal Resistance		(R)		0.15
DURABILITY	Warm Water Resistance	ASTM C1185	Physical Observations	No visible cracks or structural alteration	Pass
	Heat/Rain Resistance	ASTM C1185	Physical Observations	No visible cracks or structural alteration	Pass
			Physical Observations	No visible cracks or structural alteration	
	Freeze/Thaw Resistance ASTM C1185		Mass Loss, %	≤ 3.0%	Pass
			Freeze/Thaw, % strength retention	≥ 80%	
	UV Accelerated Weathering Test	ASTM G23	Physical Observations	No cracking, checking, or crazing	Pass
FIRE CHARACTERISTICS	Surface Burning Characteristics ASTM E84	Flame Spread Index (FSI)		0	
		Smoke Developed Index (SDI)		≤ 5	
			Fuel Contributed		0
			NFPA Class		Α
			Uniform Building Code Class	As reported	1
			International Building Code® class		Α
	Noncombustibility	ASTM E136	Noncombustible	Pass/fail	Pass
	Fire Resistance Rated Construction	ASTM E119	Fire Resistance Rating	1-hour	Note 1

Note 1: listed on Warnock Hersey and ESR 2290

Installation

Install Hardie® Plank lap siding in accordance with:

- Hardie® Plank lap siding installation instructions
- ICC-ES ESR 2290
- Requirements of authorities having jursidiction

Warranty

Hardie® Plank lap siding: 30-year, Non-Prorated, Limited Warranty ColorPlus® Technology: 15-year Limited Finish Warranty

Sustainable Design Contribution

- Regionally sourced content- varies by project location
- Avoidance of certain chemicals or Red List Compliance

Detailed product information for LEED projects, or other state or regional sustainability programs is available through James Hardie Technical Services.

Storage and Handling

Store flat and keep dry and covered prior to installation.

Technical Services

Contact James Hardie Technical Services online at JamesHardie.com, or by phone at (800)426-4051

SS2001 02/24 PAGE 2 OF 2

IMPORTANT: Failure to install and finish this product in accordance with applicable building codes and James Hardie written application instructions may affect system performance, violate local building codes, void the product-only warranty and lead to personal injury. DESIGN ADVICE: Any information or assistance provided by James Hardie in relation to specific projects must be approved by the relevant specialists engaged for the project eg. builder, architect or engineer. James Hardie will not be responsible in connection with any such information or assistance.

